Featuring GIO Veneto, Bianco 2 ft x 4 ft

GIO
ARCHITECTURAL TILE + STONE

# veneto

A chic porcelain tile emerges at the intersection of concrete's industrial style and limestone's perpetual appeal; neutral colors, generous sizes and trims–a complete foundation for modern design

## INKJET COLOR BODY RECTIFIED FLOOR & WALL GLAZED PORCELAIN STONEWARE

## TAUPE



**GIVNT2448TP**
24" x 48" Rectified Field Tile



**GIVNT2424TP**
24" x 24" Rectified Field Tile



**GIVNT1224TP**
12" x 24" Rectified Field Tile



**GIVNT324BNTP**
3" x 24" Bullnose



**GIVNT624TP**
6" x 24" Rectified Field Tile



**GIVNT612CBTP**
6" x 12" Cove Base



**GIVNTMOSTP**
2" x 2" Mosaic

## BIANCO



**GIVNT2448BI**
24" x 48" Rectified Field Tile



**GIVNT2424BI**
24" x 24" Rectified Field Tile



**GIVNT1224BI**
12" x 24" Rectified Field Tile



**GIVNT324BNBI**
3" x 24" Bullnose



**GIVNT624BI**
6" x 24" Rectified Field Tile



**GIVNT612CBBI**
6" x 12" Cove Base



**GIVNTMOSBI**
2" x 2" Mosaic

## LIGHT GREY



**GIVNT2448LG**
24" x 48" Rectified Field Tile



**GIVNT2424LG**
24" x 24" Rectified Field Tile



**GIVNT1224LG**
12" x 24" Rectified Field Tile



**GIVNT324BNLG**
3" x 24" Bullnose



**GIVNT624LG**
6" x 24" Rectified Field Tile



**GIVNT612CBLG**
6" x 12" Cove Base



**GIVNTMOSLG**
2" x 2" Mosaic

### PACKAGING

| NOMINAL SIZE | PIECES PER BOX | SQ. FT. PER BOX | LBS. PER BOX | BOXES PER PALLET | SQ. FT. PER PALLET | WEIGHT PER PALLET |
|---|---|---|---|---|---|---|
| 24" x 48" Rectified Field Tile | 2 | 15.51 | 62.81 | 35 | 542.85 | 2200 |
| 24" x 24" Rectified Field Tile | 3 | 11.63 | 47.62 | 40 | 465 | 1904.77 |
| 12" x 24" Rectified Field Tile | 7 | 13.56 | 55.55 | 40 | 542.51 | 2222 |
| 6" x 24" Rectified Field Tile | 12 | 11.63 | 47.62 | 40 | 465 | 1904.77 |
| 2" x 2" Mosaic | 10 | 9.69 | 40 | - | - | - |
| 3" x 24" Bullnose | 10 | - | 20 | - | - | - |
| 6" x 12" Cove Base | 20 | - | 40 | - | - | - |

### TECHNICAL SPECIFICATIONS

| DESCRIPTION | RESULT | TEST METHOD (STANDARD) |
|---|---|---|
| Chemical Resistance | RESISTANT | C650 Test |
| Water Absorption | 0.5% | C373 Test |
| PEI | 4 | C1027 Test |
| C.O.F. (Dynamic) | 0.42 | ANSI 137.1 |
| Frost Resistance | RESISTANT | ASTM C1026 |
| Breaking Strength | 250 | ASTMC648 |
| Thickness | 9 mm | Factory Provided |

### SHADE VARIATION AND APPLICATIONS

V2



MODERATE VARIATION

| | RESIDENTIAL | COMMERCIAL | INDUSTRIAL |
|---|---|---|---|
| Floor | • | • | • |
| Wall | • | • | • |
| Countertop | • | • | • |