

Featuring GIO Forza, Taupe 24x24

forza

GIO
ARCHITECTURAL TILE + STONE

forza

The strong but not so silent type, as each tile tells the story of weathered stone–rich with visual depth, natural contrasts, and earthen hues

INKJET COLOR BODY RECTIFIED FLOOR & WALL GLAZED PORCELAIN STONEWARE


IVORY



GIFO2424IV
24" x 24" Rectified Field Tile



GIFO1224IV
12" x 24" Rectified Field Tile



GIFOMOSIV
12" x 12" Mosaic




GIFO424BNIV
4" x 24" Bullnose


BLACK



GIFO2424BL
24" x 24" Rectified Field Tile



GIFO1224BL
12" x 24" Rectified Field Tile




GIFOMOSBL
12" x 12" Mosaic




GIFO424BNBL
4" x 24" Bullnose


GREY



GIFO2424GR
24" x 24" Rectified Field Tile



GIFO1224GR
12" x 24" Rectified Field Tile



GIFOMOSGR
12" x 12" Mosaic




GIFO424BNGR
4" x 24" Bullnose


TAUPE



GIFO2424TP
24" x 24" Rectified Field Tile



GIFO1224TP
12" x 24" Rectified Field Tile



GIFOMOSTP
12" x 12" Mosaic



GIFO424BNTP
4" x 24" Bullnose

PACKAGING


NOMINAL SIZE	PIECES PER BOX	SQ. FT. PER BOX	LBS. PER BOX	BOXES PER PALLET	SQ. FT. PER PALLET	WEIGHT PER PALLET
24" x 24" Rectified Field Tile	4	15.63	65	36	562.68	2340
12" x 24" Rectified Field Tile	8	15.61	65	32	495.04	2080
12" x 12" Mosaic	4	3.87	18.38	90	-	-
4" x 24" Bullnose	12	-	34.17	60	-	-

TECHNICAL SPECIFICATIONS

DESCRIPTION	RESULT	TEST METHOD (STANDARD)
PEI Rating	4	ASTM C-1027
Water Absorption	0.5%	ASTM C-373
C.O.F. (Dynamic)	0.42	ANSI A137.1
Chemical Resistance	Excellent	ASTM C650
Frost Resistance	Resistant	ASTM C1026
Thickness	9 mm	Factory Provided

SHADE VARIATION AND APPLICATIONS

V3



HEAVY VARIATION

	RESIDENTIAL	COMMERCIAL	INDUSTRIAL
Floor	•	•	•
Wall	•	•	•
Countertop	•	•	•